

SILICONE SEALANT(RTV-1)

NAME	FEATURE	DENSITY	VISCOSITY	EXTRUSION ABILITY BY 3 BAR G/MIN.	SKIN-CURING TIME MIN.	SHORE A HARDNESS	TENSILE STRENGTH, MPA	ELONGATION @ BREAK. %	TEARSTRENGTH KN/M	TEMP. RESISTENS °C	BASE
M 88	Standard low cost	1,02	thix.	66	5	12	2,2	800		-50-150°c	Acetic
A 8	High temperature resistant Chemical resistant.	1,05	thix.	6	3	22	5	700	12	-70-275°c	Acetic
S 8	Sanitary (glasclear)	1,02	thix.	96	10	14	2,2	550		-70-250°c	Acetic
N 8	Free of smell for indoor use	1,23	thix.	20	5-10	23	2,4	452	2,8	-50-150°c	Oxim